

UNDERLAY TECHNICAL SPECIFICATION

FIREGUARD 8

Product Code: FG8 Origin: Malaysia

Manufacturer: Lien Huat Alliance Sdn. Bhd.

PRODUCT SPECIFICATIONS

Construction : Waffle Sponge

Raw Material : 100% Natural Rubber

Width : 1.37 m (4.49')Length : 11.0 m (36.09')**Roll Size** : 15.07 m² (18.08 yd^2) Weight : 3451 g/m² (101.78 oz / yd²) **Density** : 431.38 kg/m³ (26.93 lbs / ft³) Nominal Thickness: 8.0 mm ± 0.5 mm $(0.31" \pm 0.02")$

Colour : Brown

Backing Materials: Polyester Spunbonded Fabric /

Stitchbonded Paper



PRODUCT DESCRIPTION

The Fireguard Series is based on the small bubble waffle sponge profile, which gives it a perfect balance between comfort and dimensional stability. Its added feature is in its inherent flame retardant properties. Unlike most flame retardant underlays which ignites but burns within a confined area and extinguishes after a while, Fireguard does not combust and does not use any hazardous flame retardant chemicals.

RECOMMENDED APPLICATIONS

Sectors: Hospitality, Commercial

Areas: Hotels, Cinemas, Restaurants, Convention Halls, "Areas where public safety is a concern"

Top Surface: Broadloom Carpets, Area Rugs

Installation Method: Install with fabric-side facing up; suitable for stretch-fit installation of Carpets

SUMMARY OF TESTS (results on next page)

End use classification: Class HC/U; Heavy Contract Use

Material Standards

Environmental / Flammability Standards

BS 5808 / BS EN 14499 REACH EU Compliant

BS 4098

BS 4051 / ISO 1765 BS 4052 / ISO 2094

BS 4939 / ISO 3416

BS 2576 / BS EN ISO 13934

BS 4790

Disclaimer

- 1. Some test results were derived from similar product results
- 2. Fireguard and associated labels are trademark of Lien Huat Alliance Sdn Bhd
- 3. Densities are indicative values only as there may be slight variations within normal manufacturing tolerance due to the product being made from natural materials. However, such variations will not affect the quality and performance of the product.

Lot 9083, Jalan Udang Galah, Telok Gong, 42000 Port Klang, Selangor, Malaysia

T: +60 3 3134 3902 F: +60 3 3134 3903 E: info@lienrub.com www.lienhuat.com





UNDERLAY TECHNICAL SPECIFICATION

FIREGUARD 8

Test Performance to BS 5808: 1991 / BS EN 14499: 2015

| End Use Classification | Class HC/U; High Contract Use | |
|---|-------------------------------|------------------------------|
| Work of Compression (Min 50 J/m2) | 313.5 J/m2 | BS 4098 / BS 4052 / ISO 2094 |
| Retention of Work of Compression (min 40%) | 80.0 % | BS 4098 / BS 4052 / ISO 2094 |
| Compression after Dynamic Loading | 2.0 mm | BS 4098 / BS 4052 / ISO 2094 |
| Loss in Thickness after Dynamic Loading (max 15%) | 7.6 % | BS 4098 / BS 4052 / ISO 2094 |
| Loss in Thickness after Static Loading (max 15%) | 8.5 % | BS 4939 / ISO 3416 |
| Breaking Strength - length/width (min 30N) | 86.8 N / 45.7 N | BS 2576 / BS EN ISO 13934 |
| Extension Under Force - length/width (max 15%) | 4.0 % / 2.0 % | BS 2576 / BS EN ISO 13934 |
| Resistance to Cracking (not greater than 50 mm) | Pass | BS 5808 / BS EN 14499 |

Test Performance to Environmental / Flammability Standards (BS 5808: 1991 / BS EN 14499: 2015)

Hot Metal Nut Test (Pass/Fail) Pass / Medium Radius BS 4790

Manufacturer Warranty

A manufacturer's certificate of quality and warranty is available on request. Warranty will only take into effect AFTER completion and due inspection of the project.

*This is important to ensure that you receive the authentic product and that no substitutes are used for your projects

Disclaimer

- 1. Some test results were derived from similar product results
- 2. Fireguard and associated labels are trademark of Lien Huat Alliance Sdn Bhd
- 3. Densities are indicative values only as there may be slight variations within normal manufacturing tolerance due to the product being made from natural materials. However, such variations will not affect the quality and performance of the product.



T: +60 3 3134 3902 F: +60 3 3134 3903 E: info@lienrub.com www.lienhuat.com

